

## PRODUCT DATA

**3** 03 35 00 **Concrete Finishing****LAPIDOLITH®****Concrete hardener and dustproofers****Description**

Lapidolith® is a magnesium-fluorosilicate concrete hardener and dustproofers that bonds chemically with the concrete to strengthen and harden floors that are porous, readily absorbent, and only moderately hard.

**Yield**

See Chart on page 3.

**Packaging**

5 gallon (18.93 L) pails

55 gallon (208 L) drums

Concentrate also available. Call Customer Service for more information.

**Color**

Clear liquid

**Shelf Life**

1 year when properly stored.

**Storage**

Store in original, unopened containers in cool, dry area. Protect from freezing in the container; do not store below 35° F (2° C).

**Features**

- Concrete hardener
- 100% reactive with the free lime in concrete
- Tightly binds together the cement, sand, and aggregate particles
- Nonfilm forming
- Compatible with most resilient tile adhesives

**Benefits**

- Strengthens floors that are porous, readily absorbent, and only moderately hard; ideal for aged concrete surfaces
- Produces a breathable, dense, abrasion-resistant surface
- Improves resistance to most acids, alkalis, organic and inorganic chemicals, oils, greases
- Reduces cleaning and maintenance costs for floors
- Suitable for substrates to be covered by carpeting

**Where to Use**

## APPLICATION

- Warehouses
- Aircraft hangars
- Commercial garages
- Chemical installations
- Hospitals
- Breweries
- Schools
- Dairies
- Bakeries
- Canneries
- Laundries
- Textile mills
- industrial plants
- Computer rooms under false floors

## LOCATION

- Interior and exterior

## SUBSTRATE

- Concrete

**How to Apply****Surface Preparation**

1. New concrete must be thoroughly dry and cured a minimum of 10 days; for best results cure for a full 28 days.
2. Surfaces must be clean, dry, and free of all loose dirt, oil, wax, sealers, curing and parting compounds, and other foreign matter or carbonation.
3. Use Citrus Degreaser (see Form No. 1017985) for oil stains and general cleaning. Rinse floor thoroughly and allow to dry.

**Application**

1. The number of applications and dilution ratios for Lapidolith® are dependent on the porosity and density of the concrete. Refer to coverage chart. Two applications of Lapidolith® are generally required on concrete and nonresin-based terrazzo floors. Wood-floated, broom-finished, or porous floors may require a third application applied full strength.
2. Apply Lapidolith® by roller, spray, brush, or squeegee. Bubbling indicates activation of the Lapidolith® into the concrete. Distribute evenly and mop up excess solution or puddles.

## Technical Data

### Composition

Lapidolith® is a magnesium fluosilicate hardener.

### Compliances

- Recommended for use on all classes of concrete floors as noted in Table 1.1, ACI Standard 302.1R-89
- USDA compliant for use in meat and poultry areas

### Test Data

PROPERTY	RESULTS	TEST METHODS
<b>Abrasion resistance</b> , depth of wear, in (mm) ASTM C 779*		
30 minutes		
Untreated concrete	0.0264 (0.7)	
Lapidolith® treated*	0.0025 (0.06)	
<b>Abrasion resistance</b> , depth of wear, in (mm) ASTM C 779*		
60 minutes		
Untreated concrete	0.0428 (1.1)	
Lapidolith® treated*	0.0106 (0.27)	

\*Concrete was cured for 28 days.

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

### Chemical Resistance

ACI Standard 302.1R-89 magnesium fluorosilicate hardeners can be used to increase concrete resistance to chemicals including, but not limited to the following:

Aluminum sulfate	Mercuric chloride	Sulfite liquor
Ammonium chloride	Mercurous chloride	Tallow and tallow oil
Barium hydroxide	Mine water, waste	Tannic acid
Beef fat	Mineral oil	Tanning liquor, 10%
Calcium hydroxide	Molasses	Tobacco
Calcium nitrate	Mustard oil	Walnut oil
Carbon dioxide	Nickel sulfate	Zinc chloride
Carbonic acid	Oleic acid, 100%	Zinc sulfate
Castor oil	Olive oil	Zinc nitrate
Coal-tar oils	Paraffin	Zinc sulfate
Cottonseed oil	Phenol, 25%	
Creosote	Phosphoric acid, 85%	
Cresol	Pickling brine, 10%	
Distillers slop	Poppy seed oil	
Ethylene glycol	Potassium aluminum sulfate, 10%	
Ferric chloride	Potassium carbonate	
Ferric sulfate	Potassium chloride	
Ferrous chloride	Potassium dichromate	
Ferrous sulfate	Potassium persulfate	
Fish oil	Potassium sulfate	
Fruit juices	Rapeseed oil	
Glucose	Sea water	
Glycerine	Silage	
Hydrogen sulfide	Sodium bromide	
Iodine	Sodium carbonate	
Lactic acid, 25%	Sodium chloride	
Lead refining solutions, 10%	Sodium dichromate	
Lignite oils	Sodium nitrite	
Machine oils	Sodium sulfate, 10%	
Magnesium chloride	Sodium sulfite, 10%	
Magnesium sulfate	Sodium thiosulfate	
Manganese sulfate	Soybean oil	
Manure	Sugar	
Mash, fermenting		

## Yield

TYPE OF SURFACE	FT <sup>2</sup> /GAL (M <sup>2</sup> /L) (MIXED MATERIAL)	APPLICATIONS	DILUTION RATIO (BY VOLUME)	
			WATER TO LAPIDOLITH®	RATIO
Light to moderately troweled floors	100 (2.45)	2	1 to 1 first 1 to 2 second	1.17
Heavy-duty or densely troweled floors	100 – 300 (2.45 – 7.35)	2	3 to 1 first 1 to 2 second	0.92
Rough-finished floors	100 (2.45)	2	1 to 1 first 1 to 2 second	1.17
Terrazzo (nonresin based)	300 (7.35)	2	3 to 1 each	0.50
Concrete, polished sheen	200 – 300 (4.9 – 7.35)	3	4 to 1 first 3 to 1 second 2 to 1 third	0.78

To estimate the quantity of Lapidolith® needed for an application, divide the area of the floor by the coverage rate (ft<sup>2</sup>/gal or m<sup>2</sup>/L) of mixed material. Multiply this number by the ratio (in last column). Example: 8,000 ft<sup>2</sup> floor, moderately troweled: 8,000 ÷ 100 = 80 gallons mixed material x 1.17 = 93.6 gallons of Lapidolith® needed.

Recommendations for the number of applications and the dilution ratios are based upon average conditions. Coverage varies with application method, porosity, and texture of concrete.

### CONCRETE

1. After the first application, allow the floor to dry until no longer visibly wet.
2. If crystals develop during the second application, flush the surface liberally with clean water, preferably hot. At the same time, rapidly brush the floor with a stiff-bristled broom. Then mop up excess water and allow the surface to dry.

### CONCRETE, POLISHED SHEEN

1. To achieve the appearance of a polished sheen from traffic, use 3 applications of Lapidolith®. The first is diluted 4 to 1 (water to Lapidolith®), the second is diluted 3 to 1, and the third is diluted 2 to 1 (see Yield section).
2. As the last application is drying, wait for the uniform appearance of white crystals. Flood the floor with water and buff with a commercial floor buffer using a 3M® or similar type of abrasive pad. Continue buffing until the floor acquires a patina or polish and the whiteness is gone.
3. The above recommendation is for dense, steel-troweled floors. Older or more porous concrete may require less dilution or a lower coverage rate or more than 3 applications.

CAUTION: unusually wet or oily environments will be more slippery with this surface treatment.

### TERRAZZO (NONRESIN BASED)

1. Do not allow the first application to dry. While the surface is still damp, flush it thoroughly with clean hot water and then allow it to dry until no longer visibly wet. For the second application, follow the same procedure but mop up excess wash water and allow the surface to dry.
2. White crystals developing after the first or second application signifies too strong a mix or the surface reaching maximum hardness. If this occurs, stop the application and flush the surface with clean, hot water; broom with a stiff-bristle broom, and allow to dry. If any applications remain, increase the dilution ratio to avoid further problems.

### Clean Up

Clean all tools and equipment with water immediately after use. Dispose of unused material according to local regulations.

### Maintenance

1. Routine sweeping and washing of floors with mild conventional cleaners and detergents is recommended.
2. Remove all abrasive grit and wipe up corrosive spills as soon as possible.

### For Best Performance

- In event of freeze/thaw, warm and restir to uniformity. If separation is persistent, discard Lapidolith®—DO NOT APPLY.
- When mixing or handling Lapidolith® in other than the original sealed container, use a plastic bucket.
- Small amounts of sediment or a cloudy appearance in the container will not affect product performance.
- Do not apply to uncured concrete; concrete must be properly wet cured.
- Do not apply Lapidolith® to floors that have been previously sealed or treated with curing and parting compounds unless these products have been chemically or mechanically removed.
- Lapidolith® can be used for exteriors. If the surface has been steel troweled, however, traffic can polish the surface and make it slippery.
- Although Lapidolith® is chemically resistant, its application in specific chemical environments should be checked with BASF Technical Service.
- For resilient tile applications, conduct an adhesion test.
- Never use Lapidolith® with plastic concrete or mortar or resin-based terrazzo mixes.

- Lapidolith® will not salvage honeycombed or structurally unsound surfaces.
- Do not allow Lapidolith® to dry on terrazzo (resin-based) floors except as indicated in application instructions.
- Do not allow Lapidolith® to come in contact with any glass, fabric, metal, or painted surfaces. Immediately wipe contaminated surfaces with a clean water-saturated cloth, then wipe dry with a second clean cloth.
- For subsequent coatings applications, perform proper surface preparation and consult the coating manufacturer for more instructions.
- When a curing compound must be applied to freshly placed concrete, use a nonfilm-forming curing compound such as Sonneborn's Kure-N-Harden™. Kure-N-Harden™ not only cures, but surface hardens concrete to some degree; consequently, somewhat less than the recommended 2 applications of Lapidolith® will sufficiently harden the concrete.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

## Health and Safety

LAPIDOLITH®

### Danger—Corrosive

Lapidolith® contains magnesium fluorosilicate and sulfuric acid.

### Risks

Contact with skin or eyes may cause burns. May be absorbed through skin. Repeated or prolonged exposure increases the risk of absorption. Inhalation of vapors may cause irritation. May cause irritation and burns of mouth, throat and stomach. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

### Precautions

KEEP OUT OF THE REACH OF CHILDREN. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. DO NOT take internally. Prevent inhalation of vapors or mists. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or if used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. Empty container may contain hazardous residues. All label warnings must be observed until container is commercially cleaned or reconditioned.

## First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. Remove and wash contaminated clothing. If irritation persists, SEEK MEDICAL ATTENTION. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

### Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects, or reproductive harm.

### VOC Content

0 lbs/gal or 0 g/L, less water and exempt solvents.

**For medical emergencies only,  
call ChemTrec (1-800-424-9300).**

## BASF Construction Chemicals, LLC – Building Systems

889 Valley Park Drive  
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

**Customer Service** 800-433-9517  
**Technical Service** 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

**For professional use only. Not for sale to or use by the general public.**