

Sikadur® 42, Grout-Pak

Pre-proportioned, epoxy, baseplate grouting system

Construction

Description	Sikadur 42, Grout-Pak is a 3-component, 100% solids, moisture-tolerant, epoxy baseplate grouting system.
Where to Use	<ul style="list-style-type: none"> ■ Precision seating of baseplates. ■ Precision grouting of wind turbine tower bases requiring rapid strength gain. ■ Grouting under equipment, including heavy impact and vibratory machinery, reciprocating engines, compressors, pumps, presses, etc. ■ Grouting for "pour-back" anchorage on post tensioning projects (e.g. segmental bridge). ■ Grouting under crane rails.
Advantages	<ul style="list-style-type: none"> ■ Ready to mix, pre-proportioned kit ■ Moisture-tolerant ■ Corrosion and impact resistant ■ Stress and chemical resistant ■ Long working time ■ High vibration resistance ■ Fast strength gain ■ Low peak exothermic system for large pours ■ High effective bearing area ■ Excellent flowability ■ USDA certifiable
Packaging	<p>0.5 cu. ft. kit: Contains 0.9 gal. epoxy (Component A and Component B in a 5 gal. pail separated with a topline), and 50 lbs. aggregate (Component C) in a multi-wall bag.</p> <p>1.5 cu. ft. kit: Contains 2.7 gal. epoxy (Component A in a 5 gal. pail and Component B in a 2 gal. pail) and 150 lbs. aggregate (Component C) in three 50 lb. multi-wall bags.</p>

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	2 years in original, unopened containers.		
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-85°F (18°-29°C) before using. Component C must be kept dry.		
Color	Concrete gray		
Consistency	Flowable		
Application Life	Approximately 90 minutes		
Tensile Properties (ASTM C-307) 7 day	Tensile Strength	2,300 psi (15.8 MPa)	
Flexural Properties (ASTM C-580)			
7 day	Flexural Strength (Modulus of Rupture)	4,000 psi (27.6 MPa)	
	Tangent Modulus of Elasticity	1.30 x 10 ⁶ psi (8,963 MPa)	
Water Absorption (ASTM C-413) 7 day (2-hour boil)	0.04%		
Bond Strength (ASTM C-882 modified)			
7 day	Bond Strength to Concrete	4,200 psi (29.0 MPa)	
	Bond Strength to Steel	3,800 psi (26.2 MPa)	
Coefficient of Thermal Expansion (ASTM C-531)	24.5 x 10 ⁻⁶ in./in./°F (13.7x10 ⁻⁶ mm/mm/°C)		
Thermal Compatibility (ASTM C-884)	passes test		
Effective Bearing Area¹	>95%		
Compressive Properties (ASTM C-579B): Compressive Strength, psi (MPa)			
	40°F* (4°C)	73°F* (23°C)	90°F* (32°C)
8 hour	-	-	5,500 (37.9)
16 hour	-	9,600 (66.2)	9,800 (67.6)
1 day	-	12,200 (84.1)	11,500 (79.3)
3 day	4,800 (33.1)	14,000 (96.6)	14,000 (96.6)
7 day	13,700 (94.5)	14,900 (102.8)	14,800 (102.1)
14 day	13,900 (95.9)	15,000 (103.4)	15,200 (104.8)
28 day	13,900 (95.9)	15,200 (104.8)	15,600 (107.6)

* Material cured and tested at the temperatures indicated.

¹ Percent final surface area of grout in contact with bearing plate



How to Use

Surface Preparation

Substrate and baseplate contact area must be clean, sound, and free of standing water. Remove dust, laitance, oils, grease, curing compounds, waxes, impregnations, foreign particles, coatings and disintegrated materials by mechanical means (i.e., sandblasting, bush hammering). Sandblast metal baseplates to a commercial white finish for maximum adhesion. Apply grout immediately to prevent re-oxidizing. Concrete substrate shall have reached its desired strength (3,000 psi minimum) and must be dimensionally stable.

Forming

The flowable consistency of the epoxy adhesive grout system requires the use of forms to contain the material around the baseplates. In order to prevent leakage or seepage, completely seal all forms. Apply polyethylene film or wax to all forms to prevent adhesion of the grout. Prepare form work to maintain a 2 in. (50 mm) liquid head to facilitate placement. A grout box that can be attached to the form will enhance the grout flowability. Projected anchor bolts should be wrapped with neoprene foam rubber (or similar) to prevent grout from adhering to the bolts. The use of expansion joints is recommended on large pours to minimize the potential for cracking in the epoxy grout (maximum 3-4 ft. spacing in each direction).

Mixing

0.5 cu. ft. kit: Pour the entire contents of Components 'A' & 'B' into an appropriate mixing vessel (e.g. 5 gal. bucket) and mix for 30 seconds with a 1/2 in. Jiffy mixing paddle (5 in. blade diameter) on a low-speed (400 - 600 rpm) 3/4 in. drive rotary drill, taking care not to entrain air during mixing. Do not over-mix. It is critical to the performance of the grout that there be no appreciable air bubbles in the resin. Slowly add the entire contents of Component 'C' and mix until uniformly blended (approx. 5 minutes).

1.5 cu. ft. kit: Pour the entire contents of Components 'A' & 'B' into an appropriate mixing vessel (e.g. 5 gal. bucket) and mix for 30 seconds with a 1/2 in. Jiffy mixing paddle (5 in. blade diameter) on a low-speed (400 - 600 rpm) 3/4 in. drive rotary drill, taking care not to entrain air during mixing. Do not over-mix. It is critical to the performance of the grout that there be no appreciable air bubbles in the resin. Transfer the mixed resin to an appropriate mixing vessel. Slowly add the entire 3 bags of Component 'C' and mix until uniformly blended (approx. 5 minutes).

Application

Pour the mixed grout into the prepared forms from one side only to eliminate air entrapment. Baseplate should have vent holes around periphery to prevent air pockets from developing. Maintain the liquid head to ensure intimate contact with the base plate. Plungers may be used to ease placement. Place sufficient epoxy adhesive grout in the forms to rise slightly above the underside of the base plate. Grout depth of 1 in. (25 mm) minimum required.

Limitations

- Minimum substrate and ambient temperature is 40°F (4°C).
- Do not thin. Addition of solvents will prevent proper cure.
- Material is a vapor barrier after cure.
- Minimum grout depth is 1 in. (25 mm).
- Baseplate should be shielded from direct sunlight and rain for a minimum of 24 hours before epoxy grouting, and 48 hours after grouting.
- Maximum grout depth is 4 in./lift (101 mm).
- Component C must be kept dry.
- Cold material may require chaining, rodding, and pushing during placement.
- For proper seating, allow grout to rise above the bottom of the base plate.
- **DO NOT BATCH. MIX COMPLETE UNITS.**
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.

Caution

Component A - WARNING: IRRITANT: - Contains Aromatic Hydrocarbons (CAS: 68477-31-6) and Modified Epoxy Resin (Mixture). Causes eye irritation. May cause skin/respiratory tract irritation. Aspiration hazard if swallowed.

Component B - WARNING: IRRITANT: - Contains Aromatic Hydrocarbons (CAS:68477-31-6), Benzyl Alcohol (CAS: 100-51-6), Nonyl Phenol (CAS:25154-52-3) and Amines (Mixture). Causes respiratory tract irritation. May cause eye/skin irritation. Harmful if swallowed.

Component C: WARNING: IRRITANT: - Contains Polyvinyl Chloride (CAS:9002-86-2), Silica Quartz (CAS: 14808-60-7) and Titanium Dioxide (CAS: 13463-67-7). Causes eye irritation. May cause skin/ respiratory tract irritation. Breathing dust may cause nose, throat or lung irritation. Respirable crystalline silica can cause silicosis, a fibrosis of the lungs.

WARNING: This product contains a chemical known to the State of California to cause cancer.

First Aid

In case of skin contact, wash immediately and thoroughly with soap and water. If symptoms persist, consult a physician. For eye contact, flush immediately with plenty of water for at least 15 minutes, contact a physician. For respiratory problems, remove person to fresh air; if symptoms persist, contact a physician. In case of ingestion, dilute with water and consult physician. Remove contaminated clothing.

Clean Up

In case of spills or leaks, wear suitable protective equipment, contain spill, collect with absorbent material, and transfer to suitable container. Ventilate area. Avoid contact. Dispose of in accordance with current, applicable local, state and federal regulations.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikausa.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikausa.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikausa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikadur are registered trademarks.
Printed in Canada.

